



## BLUEMINT

### DESCRIPTION

These nitrile disposable gloves are powder free, and 2.2 Mil in thickness.

- Non Sterile Examination Gloves,
- Nitrile Synthetic, No NRL Protein
- Powder Free and 100% Latex free
- Beaded Cuff

### RECOMMENDATION

- Handling of cytostatics
- Handling oils, acids, caustics and alcohols
- Laboratory analysis
- Painting and spraying
- Chemical handling
- Emergency response (EMS and EMT)
- Maintenance work

### PRODUCT INFORMATION

<b>Material</b>	100% Nitrile
<b>Colour</b>	Blue
<b>Packaging</b>	100 Ambidextrous gloves per box, 1000 per case
<b>Sizes</b>	7-10

### CERTIFICATION

89/686/EEC, 93/42/EWG  
ISO 9001:2008, ISO 13485, CMDCAS 13485  
(SGS) EN 455 1-4  
EN 420 : 2003 + A 1 : 2009  
EN 374 2-3, EN 388  
EN 1186: Food Contact Approved (SGS)



## OTHER INFORMATION

Glove can be used for touchscreen applications.

There is no need to remove the gloves when using touchscreen panels, as the operator can operate freely with the product on.

## CLEANING / MAINTENANCE

Both new and used gloves should be thoroughly inspected before being worn to ensure no damage is present. Gloves should not be left in a contaminated condition if reuse is intended in which case gloves should be cleaned as far as possible. Gloves may be washed after removal with mild detergent solution at a temperature not exceeding 40 Deg C and allowed to dry naturally, ideally with some air movement.

## STORAGE

Gloves should be ideally stored in cool dry conditions in the original package and out of direct sunlight.

## OBSOLESCENCE

When stored as recommended will not suffer change in mechanical properties for up to 5 years from the date of manufacture. Service life cannot be specified and depends on the application and responsibility of the user to ascertain the suitability of the glove for the intended use.

## GENERAL

None of the materials or processes used in the manufacture of these products are known to be harmful to the wearer.

## PLEASE NOTE

The results of physical tests should help in glove selection, however it must be understood that actual conditions of use cannot be simulated and it is the responsibility of the end user and not the manufacturer to determine glove suitability for the intended use.

## Washing

Please do not exceed temperatures of 30 C centigrade.

## PRODUCT INFORMATION:

Freedom from Holes

(Inspection level I) 1.5 AQL ASTM D5151/EN 374-2

Palm Thickness Single Wall (mm: 0.12) / (mils: 3.2)

ASTM D3767/EN 420

## BEFORE AGING AFTER AGING

Ultimate Tensile Strength > 14 Mpa > 14 Mpa ASTM D 412-06a Elongation at Break (%) > 500 > 400 ASTM

D 412-06a

Force at break (N) > 6 > 6 EN 455-2

## PROPERTY TYPICAL VALUES TESTING METHOD

91/2-10

Length (mm) 240