

Temperature (C)	Thermal Conductivity (Watts/m * K)	Source
244	43.12	1
283	46.9	2.1A
289	48.46	1
298	46.6	2.1A
306	46	2.1A
320	47.5	2.1A
323	44.9	3.1
327	44.6	3.1
336	47.4	2.1A
342	44.9	3.1
351	48.4	2.1A
358	45.7	3.2
360	46.4	3.2
376	46.4	3.2
378	46	3.1
379	46.7	3.1
383	45.7	3.1
397	48.12	1
418	47.4	3.2
418	48.3	3.2
422	47.8	3.2
445	49.63	1
447	46.49	1
449	48	1
449	47.5	3.1
450	47.9	3.1
451	46	2.2A
451	47.9	2.2B
467	47.8	2.2A
467	49.6	2.2B
490	51.8	2.1A
490	52.2	2.1B
498	49.7	3.2
498	50	3.2
505	52.2	2.1A
505	52.3	2.1B
517	50.79	1
518	50.6	2.1A
518	50.2	2.1B
525	50.44	1
529	47.65	1
533	48.23	1
533	49.9	2.1A
533	49.3	2.1B
536	48.46	1
536	47.7	2.2A
536	48.6	2.2B
552	55.8	3.1

555	50	2.2A
555	50.4	2.2B
568	45.56	1
600	58.7	3.2
646	52.1	2.2A
646	52.1	2.2B
663	52.7	2.2A
663	52.7	2.2B
664	55.2	3.1
670	56.2	3.1
673	55.5	3.1
674	53.4	2.1A
674	54.8	2.1B
683	50.44	1
683	48.58	1
686	54.4	2.1A
686	56.4	2.1B
715	58.6	3.2
720	58.5	3.2
724	58.7	3.2
767	54.7	2.2A
778.4	54.9	3.1
784	56	2.2A
784	57	2.2B
789	50.9	1
795	51.83	1
830	58.2	3.2
839	52.65	1
886	53.35	1
899	53.58	1
920	55.79	1
964	59.4	2.1A
964	60.1	2.1B
985	60.8	2.1A
985	61	2.1B
1020	61.3	2.1A
1020	61.3	2.1B
1040	61.1	2.1A
1040	59.9	2.1B
1080	58.9	2.1A
1080	58.9	2.1B
1100	61.1	2.1A
1100	61.4	2.1B
1121	60.1	2.1A
1121	60.4	2.1B
1140	60.78	2.1A
1140	60.8	2.1B

## Sources

1. T. B. Douglas, et al.,  
"Lithium: Heat Content from 0 to 900°, Triple Point and Heat of Fusion,  
and Thermodynamic Properties of the Solid and Liquid,"  
J. Am. Chem. Soc., 77(8), pp. 2144-2150 (1955).
2. I. I. Novikov, et al.,  
Thermophysical Properties of Liquid Alkali Metals at High Temperatures,  
High Temperature, 7, pp. 65-68 (1969).
3. P. Y. Achener and D. L. Fischer,  
Alkali Metals Evaluation Program:  
The Specific Heat of Liquid Sodium and Lithium,"  
Aerojet General Report AGN 8191, Vol. 6, (1967) N67-38991.